

TOP GREYGREEN OXIDE 437

This is an economical metal primer for ferrous substrate both interior and exterior applications.

Colour	Greygreen	
Pack Size	1, 5 and 18 litres	
Composition	<i>Binder</i>	Alkyd and hydrocarbon derivative
	<i>Pigment</i>	Iron oxide and inert mineral extenders
	<i>Solvent</i>	Hydrocarbon mixture
Volume Solid	65 ± 2%	
Recommended Dry Film thickness	35 – 45 microns (per coat)	
Drying Times *	<i>Touch Dry</i>	Within 4 hour
	<i>Hard Dry</i>	Within 8 hours
Full Cure *	3 – 4 weeks; Time for the coating to reach its full chemical/ mechanical properties and will resist and perform as per the properties featured	
Over-coating Interval *	Minimum 16 hours	
Spreading Rate *	12 – 15 m ² / litre/ coat	
Application	<i>Brush/Roller</i>	Use as is, thin not exceeding 5% by volume with paint thinner or white spirit/ mineral turpentine if necessary
	<i>Conventional Spray</i>	Thin with paint thinner or white spirit/ mineral turpentine to 20% by volume
	<i>Airless Spray</i>	Use as is
Surface Preparation	<u><i>New Unpainted Surface</i></u>	<u><i>Previous Painted Surface</i></u>
	Ferrous - Remove rust or mill scales by manual or mechanical cleaning - Ensure surface free from oil, grease and other contaminant	- Remove loose adhering paint - Remove debris, oil, grease or other contaminant before painting
Recommended Painting System	<u><i>Sequence</i></u>	<u><i>Product</i></u>
	Primer (1 coat)	TOP Greygreen Oxide 437
	Undercoat (1 coat)	TOP Cat Kilat Undercoat
	Finish	TOP Cat Kilat

* Based on recommended thickness; will vary considerably with surface characteristics, application techniques, weather and wastage.

The corresponding Safety Data Sheet (SDS) for this product shall be provided upon request.

Further inquiry and SDS request can be made to transpaint@yungkong.com

Manufactured by: **Trans Paint Coatings Sdn Bhd**. Lot 1393, Jalan Meranti, Bintawa Industrial Estate, 93450 Kuching, Sarawak, Malaysia.

Tel: +6082 334 222 Fax: +6082 339 189 Website: www.transpaint.yungkong.com

While every care has been taken to ensure the accuracy of the information contained in this data sheet, it is provided in good faith and that no liability can be accepted arising from its use. Where the conditions of use warrant it, it is recommended that the data are checked to ensure their suitability for the use envisaged.

Revision: **19 Nov 2019**

<end of document>