

PLUSS ROAD LINE

This is an alkyd/chlorinated rubber based coating for the marking of concrete and asphalt surfaces. It is fast drying and has high chemical resistance and recoating properties.

Standard	Equivalent to Malaysian Standard 164:1991	
Colour	White, Yellow and Black (non-reflective)	
Pack Size	5 litres	
Composition	<i>Binder</i>	Alkyd/Chlorinated rubber
	<i>Pigment</i>	Titanium dioxide and mineral extenders
	<i>Solvent</i>	Hydrocarbon mixture
Volume Solid	Average 62 ± 2%, varying with colours	
Recommended Dry Film thickness	50 – 60 microns (per coat)	
Drying Times *	<i>Touch Dry</i>	Within 1 hour
	<i>Hard Dry</i>	Within 2 hours
Full Cure *	3 – 4 weeks; Time for the coating to reach its full chemical/mechanical properties and will resist and perform as per the properties featured	
Over-coating Interval *	Minimum 3 hours	
Spreading Rate *	9 – 11 m ² /litre/coat	
Application	<i>Brush/Roller</i>	Use as is
Surface Preparation	Surfaces must be clean, dry and free from loosely adhering particles. For new surfaces, 1 to 2 coats of paint are usually required.	

* Based on recommended thickness; will vary considerably with surface characteristics, application techniques, weather and wastage.

The corresponding Safety Data Sheet (SDS) for this product shall be provided upon request.

Further inquiry and SDS request can be made to transpaint@yungkong.com

Manufactured by: **Trans Paint Coatings Sdn Bhd**. Lot 1393, Jalan Meranti, Bintawa Industrial Estate, 93450 Kuching, Sarawak, Malaysia.

Tel: +6082 334 222 Fax: +6082 339 189 Website: www.transpaint.yungkong.com

While every care has been taken to ensure the accuracy of the information contained in this data sheet, it is provided in good faith and that no liability can be accepted arising from its use. Where the conditions of use warrant it, it is recommended that the data are checked to ensure their suitability for the use envisaged.

Revision: **20 JUL 2023**

<end of document>