

## NU-COTE GLAZE

This is a full acrylic emulsion finish designed for decorative effects to most surfaces. It is semi-transparent and cures to that give a brilliant pearlescent/metalline luster effect. It is suitable for both exterior and interior application. This **water-based** product features **low VOC**, **heavy-metals free** and **APEO free**, formulated with great care for your ease of mind when considering its effect to your health and the environment.

|                                       |  |  |
|---------------------------------------|--|--|
| <b>Colour</b>                         | Pearlescent – White, Silver, Violet, Orange, Pink, Green, Blue, Yellow, Indigo<br>Metalline – Gold, Bronze, Red Wine<br><i>(See Nu-Cote Glaze in Contemporary Shades 2008)</i>   |  |
| <b>Pack Size</b>                      | 300 ml   |  |
| <b>Composition</b>                    | <i>Binder</i>  | Pure acrylic emulsion  |
|                                       | <i>Pigment</i>   | Pearlescent/Metalline effect pigments  |
|                                       | <i>Solvent</i>   | Water  |
| <b>Volume Solid</b>                   | 34 ± 2% for white, varying with colours  |  |
| <b>Recommended Dry Film thickness</b> | 30 – 50 microns (per coat)   |  |
| <b>Drying Times *</b>                 | <i>Touch Dry</i>   | Within 30 minutes  |
|                                       | <i>Hard Dry</i>  | Within 1 hour  |
| <b>Full Cure *</b>                    | 3 – 4 weeks; Time for the coating to reach its full chemical/mechanical properties and will resist and perform as per the properties featured  |  |
| <b>Over-coating Interval *</b>        | Minimum 2 hours  |  |
| <b>Spreading Rate *</b>               | 7 – 11 m <sup>2</sup> /litre/coat  |  |
| <b>Application</b>                    | <i>Brush/Roller</i>  | Use as is, thin not exceeding 5% by volume with water if necessary   |
|                                       | <i>Conventional Spray</i>  | Thin with water to 10% by volume   |
|                                       | <i>Airless Spray</i>   | Thin with water to 5% by volume  |
| <b>Surface Preparation</b>            | <u><i>New Unpainted Surface</i></u>  | <u><i>Previous Painted Surface</i></u>   |
|                                       | <ul style="list-style-type: none"> <li>Ensure surface is clean and dry</li> <li>Apply appropriate sealer</li> </ul>  | <ul style="list-style-type: none"> <li>Remove loose paint film by hard scraping/high pressure water jet</li> <li>Treat fungi, algae or mould with fungicidal wash</li> <li>Ensure dry off before painting</li> </ul> |
| <b>Recommended Painting System</b>    | <u><i>Sequence</i></u>   | <u><i>Product</i></u>  |
| <i>Most Surfaces</i>                  | Primer (1 coat)  | PLUSS AP SEALER SV   |
|                                       | Finish (3 coats at least)  | <b>NU-COTE GLAZE</b>   |
|                                       | <i>Note: The colours for this product are translucent. For best result, apply over a solid base coat/primer of the same colour or white. Colours and effects depend very much on base coat/primer and the number of coats for the finishing.</i> |  |

\* Based on recommended thickness; will vary considerably with surface characteristics, application techniques, weather and wastage.

The corresponding Safety Data Sheet (SDS) for this product shall be provided upon request.

Further inquiry and SDS request can be made to [transpaint@yungkong.com](mailto:transpaint@yungkong.com)

Manufactured by: **Trans Paint Coatings Sdn Bhd**. Lot 1393, Jalan Meranti, Bintawa Industrial Estate, 93450 Kuching, Sarawak, Malaysia.

Tel: +6082 334 222 Fax: +6082 339 189 Website: [www.transpaint.yungkong.com](http://www.transpaint.yungkong.com)

While every care has been taken to ensure the accuracy of the information contained in this data sheet, it is provided in good faith and that no liability can be accepted arising from its use. Where the conditions of use warrant it, it is recommended that the data are checked to ensure their suitability for the use envisaged.

Revision: **6 NOV 2023**

<end of document>